





Fawori Decorative Coating (Line Textured)

DESCRIPTION

Cement-based, light, top coat interior and exterior coating that creates a natural texture on the surface.

APPLICATION AREAS

Used safely on finished plaster, smooth rough-cast, concrete, gas concrete or on old self-supporting silicate or acrylic-based paints for renewing or on thermal and sound insulation materials like polystyrene-based and rock wool plates.

SPECIFICATIONS

- Ideal exterior coating for thermal insulation systems with its perfect vapor permeability thanks to its cement-based special formula.
- Weather-resistant and water-repellent. Prevents moisture accumulation.
- Easy to apply and pattern due to its lightweight form.
- Adds a natural and decorative appearance to the structure. Provides a homogeneous pattern on the exterior surfaces thanks to its granule harmony.
- Hides surface defects.
- Ensures full compliance and high adherence to application surfaces.
- · No cracking and flaking.
- Pure white.

SPECIFICATIONS:

Compression Resistance: >3.0 N/mm² EN 196 Bending Resistance: >1.5 N/mm² EN 196 Impact Resistance: > 2 joule EN 13497

Thickness : Max. 3.0 mm

Fire response class: A1

COLOR

White

PEKORATIF MINERAL KAPLAMA Ceremetre Married Carrier Married Carried Married Married Carried Married Ma

SURFACE PREPARATION

Ensure the surface is clean, dry, and firm. Apply at least 48 hours after applying **Fawori Thermal Insulation Plaster** with a thickness of 4mm so that the plaster is completely dry. Ensure that **Fawori Decorative Coating Primer** is applied before coating. Cover porous and absorbent surfaces like gas concrete with **Fawori Decorative Coating** only after priming with a thin layer using thermal insulation plaster. Ensure the adherence of old paint is sound for applications on old painted surfaces.

MORTAR PREPARATION

Add clean and cold water slowly into **Fawori Decorative Coating**, and mix for approximately 10 minutes with a low speed mixer until the mixture is free of lumps. Adjust the required amount of water according to the weather conditions. Rest the mixture for 5 minutes and mix again. Readjust the consistency by adding water, if required. Mortar can also be mixed with a suitable mixing machine and applied on to the surface by spraying. Be careful not to corrode the particles inside the product while mixing with the machine. Use equal amounts of water for the mix of each mortar batch. Otherwise, pattern and tone differences may occur on the surface. Use up the prepared mixture within 2 hours depending on the weather conditions. Do not reuse the hardened material by reconstituting.

MIXING

Mix 25kg of Fawori Decorative Coating with 6.0 - 7.0L of water depending on the weather conditions.

APPLICATION

Apply the homogeneous mixture to the surface smoothly with a steel trowel or a suitable spraying machine, and remove the excesses from the surface to obtain a layer at a particle thickness. Pattern the surface within a maximum of 10 minutes after applying **Fawori Decorative Coating** to the surface in a homogeneous manner.

This product is manufactured by Betek A.Ş., with certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, TS ISO/IEC 27001.

^{*} Please contact our technical support for details that are not provided above, since this technical sheet is based on general conditions. Otherwise, the manufacturer may not be held responsible for any missing information. Our company reserves the right to change the information provided. Where necessary, please refer to the Material Safety Data Sheets for more information on health, safety and handling risks, and precautions associated with the products.



Pattern with (up-down or right-left) motions using a plastic or polyurethane trowel for a striped texture. Scrape the trowel surface frequently to obtain a good pattern. Use the products with the same batch number on the same surface. Ensure that a sufficient number of people work during the application to prevent overlapping on large surfaces, and ensure that product is applied without any break up to the joint ends or detail corners without leaving a gap.

Abstain from applying under direct sunlight, on hot surfaces heated by direct sunlight, during strong winds, fog and high relative humidity, and heavy rain. Use a protective canvas, if required. Ensure that the sub-layer and air temperatures are between +5 °C - +30 °C during the application. Moisturize the surfaces regularly by spraying (unpressurized water) to prevent a sudden loss of water and reduction in strength of the mineral coating at temperatures above 25 °C. Wait 24 hours before coloring the surface under normal conditions.

DRYING TIME

Surface dry: 24 hours at 20 °C and 65% RH. Full dry: 2-3 days. Low temperature and high relative humidity lengthen drying time.

CONSUMPTION:

Dry product consumption: 3,5 - 4,0 kg/m2

Please note that specified consumption values may vary to the surface and application conditions. Perform a controlled sample run to estimate the precise consumption.

PACKAGE

25 kg craft bag

STORAGE

It can be stored for 12 months, dry and protected from moisture.

CAUTION

There may be differences in the shades of the products due to ambient temperature, surface absorbing capacity, amount of water, mixing period, primer of the application surface, and different production batches. Ensure that **Fawori Decorative Coating Primer** is absolutely applied before coating. Ensure that **Fawori Decorative Coating Primer** that you will use must be colored approximately with ARS tubes. Paint as 2 coats both to improve the resistance of **Fawori Decorative Coating** against dirt and external effects, and to prevent shade differences arising due to various reasons. The consumption amount may differ based on pattern. Check the color before application. Buy materials based on need.

HAZARD STATEMENTS

H315 Causes skin irritation.

H318 Causes serious eye irritation.

PRECAUTIONARY STATEMENTS

P101 If medical advice is needed, keep the product container or label.

P102 Keep out of the reach of children.

P103 Read label before use.

P280 Wear protective gloves/protective clothing/eye protection/face protection.

P305 + P351 + P338 IN CASE OF EYE CONTACT: Carefully rinse with water for a couple of minutes. Remove contact lenses if worn and easy to do so. Continue rinsing.

P310 Immediately CALL NATIONAL POISON CONSULTING CENTER AT 114/Call a physician.

P321 Specific treatment required (see label).

P362 Remove your contaminated clothing and wash before reuse.

P332+P313 In case of skin irritation: Get medical advice/attention.

WARNING STATEMENT Danger

RATE NO. 10.300.1352 **POSE NO.**

15.540.1404, 15.540.1405, 15.540.1406

This product is manufactured by Betek A.Ş., with certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, TS ISO/IEC 27001.

^{*} Please contact our technical support for details that are not provided above, since this technical sheet is based on general conditions. Otherwise, the manufacturer may not be held responsible for any missing information. Our company reserves the right to change the information provided. Where necessary, please refer to the Material Safety Data Sheets for more information on health, safety and handling risks, and precautions associated with the products.





TSE

Conforms to the G communique.



Conforms to TS 7847.

Dry Film Thickness: Class E5

Granule Size: Class S4

Water Vapor Transmission Rate: Class V1 Water Transmission Rate: Class W3 Crack Coverage Capacity: Class A0 Carbon Dioxide Permeability: Class C0



GHS05

^{*} Please contact our technical support for details that are not provided above, since this technical sheet is based on general conditions. Otherwise, the manufacturer may not be held responsible for any missing information. Our company reserves the right to change the information provided. Where necessary, please refer to the Material Safety Data Sheets for more information on health, safety and handling risks, and precautions associated with the products.