



# **Fawori Pro Primer**

### PRODUCT DESCRIPTION

Acrylic copolymer emulsion-based, white-pigment, thin-layer interior primer.

#### **SPECIFICATIONS**

Increases the coating ability of the finishing coat and enables it to better stick on the surface. Thanks to its thin pattern, it creates an ideal surface for water-based paints for which brightness and texture is important, such as Fawori Silicon Silk. It increases the absorption quality of the surface and saves paint and time.

### **APPLICATION SURFACES**

Fawori Pro Primer can be applied on concrete, exposed concrete, rough-cast surfaces, MDF, precast concrete panels, OSB, brick, self -supporting previous paint (water-solvent based), and pasted surfaces.

### **APPLICATION**

Priming is carried out after the application surfaces are cleaned from any kind of mold oil, stains, dust, and loose layers. Dull the surface with sand paper before moving on to a water-based system on synthetic painted surfaces and in Silky-matt - Semi-matt - Glossy water-based systems (before primer application). Setting periods of cement-based plasters and repair materials must be observed. Ensure that the surface temperature is between +5°C and +30°C throughout application. Protect the surface from frost during primer application and drying. Apply in a single coat using a brush, roller or airless spray gun. After the application, all used tools should be cleaned with water.

Note: Apply using a wide transparent sealing tape on newly plastered surfaces. Apply the primer only after scraping, sanding, or mechanically cleaning if the plaster particles create a problem.

Our products should be applied on substructure surfaces that are built in line with General Construction Specifications dated 30.06.2007 and with No. 26568.

# **Airless Spraying:**

Pressure: 120-140 bar Nozzle Angle: 50°

Nozzle Size (inch): 0.013"

Thinning: 5%

### **THINNING**

Recommended to be applied in two coats after thinning by 10-15% with clean water in brush and roller applications.

## DRYING TIME (at 20°C, 65% RH)

First drying: 1-2 hours Paint application: 6 hours

CAUTION: Drying time is 6 hours when applied on water-based paint and 24 hours when applied on solvent-based paint (drying time can increase at higher relative humidity and lower temperature values).

# CONSUMPTION

Depending on the type, absorbency and structure of the surface to be applied, an area of  $10-15 \text{ m}^2$  can be primed with 1 liter in one coat. Perform a controlled sample run to estimate the precise consumption amount.



### **STORAGE**

It can be stored in its unopened package for 3 years, in a cool and dry place, away from frost and direct sunlight. Close the lid air-tight immediately after application.

### **PACKAGE**

20 kg -10 kg - 3.5 kg

### **WARNING STATEMENT**

Caution

### **HAZARD STATEMENT**

H317 May cause allergic skin reactions.

### **PRECAUTIONARY STATEMENTS**

P101 If medical advice is needed, keep the product container or label.

P102 Keep out of the reach of children.

P103 Read label before use.

P261 Avoid breathing its dust/fume/gas/mist/vapor/spray.

P280 Wear protective gloves/protective clothing/eye protection/face protection.

P321 Specific treatment required (see label).

P363 Wash contaminated clothing before reuse.

P333+P313 If skin irritation or itching occurs: Get medical advice/attention.

P501 Dispose of contents/container in accordance with local, regional, national and international regulations.

This technical sheet is prepared based on laboratory data under normal conditions, consult the technical personnel for details that are not provided above. Otherwise, the manufacturing company cannot be held responsible for failures that may arise due to lack of knowledge. Our company reserves the right to change the information provided.

Where necessary, please refer to Material Safety Data Sheets for more information on health, safety and handling risks, and precautions associated with the products.

This product is manufactured by Betek A.Ş. with certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, TS ISO/IEC 27001.

Rev1 March 2020