



## THERMAL INSULATION PRODUCT GROUP

# Fawori Thermal Insulation Plaster

### DESCRIPTION

**Fawori Thermal Insulation System Plaster** is a cement-based, fiber-added special plaster that is used in applying a white coat on thermal and sound insulation materials like polystyrene-based and rock wool plates in interior and exterior surfaces together with affixing these materials, and also increases the strength of the surface with mesh application.

### SPECIFICATIONS

- Strong adhesion to polystyrene-based and rock wool plates.
- Thanks to the high and healthy polymers in its formula;
  - It is secure,
  - It is resistant to impacts
  - It has high adhesion performance.
- It absorbs the tensions and vibrations resulting from temperature differences and thus minimizes the risk of cracking thanks to the fibers in its formula.
- Its long term resistance to external weather conditions is proven with hydrothermal wall test.
- It is highly water repellent.
- It has a high water vapor permeability.

### TECHNICAL SPECIFICATIONS

Adhesion (on polystyrene plate)	: > 0.08 N/mm <sup>2</sup> EN 13494
Water Absorption	: < 0,1 kg/m <sup>2</sup> .h <sup>0.5</sup> EN 1062-3
Impact Resistance	: > 2 joule EN 13497
Fire response class	: A1



### COLOR

Gray

### SURFACE PREPARATION

Ensure the surface is smooth, dry, clean, firm and self-supporting.

### MORTAR PREPARATION

Add clean and cold water slowly into **Fawori Thermal Insulation Plaster**, and mix for approximately 10 minutes with a low speed mixer until the mixture is free of lumps. Adjust the required amount of water according to the weather conditions. Rest the mixture for 5 minutes and mix again. Readjust the consistency by adding water, if required. Use up the prepared mixture within 2-2.5 hours according to the weather conditions. Do not reuse the hardened material by reconstituting.

### APPLICATION

Fasten the thermal and sound insulation materials like glued polystyrene-based and stone wool plates with dowels after a minimum of 24 hours. First install the profiles and in particular building corners, corners of openings like windows and doors, and joint gaps to suitable places. Apply **Fawori Thermal Insulation System Plaster** on thermal insulation plates in a thickness of 4 mm using a 10x10 mm toothed steel trowel. Press the alkali resistant mesh (160 g/m<sup>2</sup>) 1-1.5 mm with a trowel in a way that it will be close to the exterior surface before the plaster is fully dry by overlapping the meshes by 10 cm, and level the plaster surface. Reinforce window and door corners with crosswise mesh.

Ensure that the ambient and surface temperatures are a minimum of +5 °C and a maximum of +30 °C during application and drying. Avoid application under direct sunlight, rain and strong winds. Keep away from frost until set. Protect the application against rain or wetting due to various reasons until fully-dry. Damp the surface regularly with spraying (using unpressurized water) to prevent a sudden loss of water and enable the healthy settling of the plaster in cases where the ambient and surface temperatures exceeds +25 °C. Clean the used tools thoroughly with water after application. After the **Fawori Thermal Insulation System Plaster** application, the surface must be covered before it is exposed to extreme dew, humidity, and precipitation.

This product is manufactured by Betek A.Ş., with certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, TS ISO/IEC 27001.

\* Please contact our technical support for details that are not provided above, since this technical sheet is based on general conditions. Otherwise, the manufacturer may not be held responsible for any missing information. Our company reserves the right to change the information provided. Where necessary, please refer to the Material Safety Data Sheets for more information on health, safety and handling risks, and precautions associated with the products.



### MIXING

Mix 25kg of **Fawori Thermal Insulation System Plaster** with 5.5-6.0 L of water depending on the weather conditions.

### DRYING TIME

Surface dry: 1 day at 20 °C and 65% RH. Full dry: 2-3 days. Since drying occurs physically with the evaporation of water, low temperatures and high relative humidity lengthens this period.

### CONSUMPTION

On polystyrene plate : 4.0 - 4.5 kg/m<sup>2</sup>

On stone wool plate : 5.5 - 6.5 kg/m<sup>2</sup>

Please note that specified consumption values may vary to the surface and application conditions. Perform a controlled sample run to estimate the precise consumption.

### PACKAGE

25 kg craft bag

### STORAGE

It can be stored for 12 months in its unopened package, dry and protected from moisture.

### HAZARD STATEMENTS

H315 Causes skin irritation.

H318 Causes serious eye irritation.

H335 May cause irritation in respiratory tract.

### PRECAUTIONARY STATEMENTS

P101 If medical advice is needed, keep the product container or label.

P102 Keep out of the reach of children.

P103 Read label before use.

P261 Avoid breathing its dust/fume/gas/mist/vapor/spray.

P305 + P351 + P338 IN CASE OF EYE CONTACT: Carefully rinse with water for a couple of minutes. Remove contact lenses if worn and easy to do so. Continue rinsing.

P310 Immediately CALL NATIONAL POISON CONSULTING CENTER AT 114/Call a physician.

P321 Specific treatment required (see label).

P405 Store locked up.

P501 Dispose of contents/container in accordance with local, regional, national and international regulations.

### WARNING WORD Hazard

### RATE NO.

10.330.2505

### POSE NO.

15.335.1001, 15.335.1002, 15.335.1003, 15.335.1004, 15.335.1005, 15.335.1006, 15.335.1101, 15.335.1102, 15.335.1103, 15.335.1104, 15.335.1105, 15.335.1106, 15.335.1201, 15.335.1202, 15.335.1203, 15.335.1204, 15.335.1205, 15.335.1206, 15.340.1001, 15.340.1002, 15.340.1003, 15.340.1004, 15.340.1005, 15.340.1006



Conforms to TS 13687 / 2016 and TS EN 13500.

GHS05

GHS07



This product is manufactured by Betek A.Ş., with certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, TS ISO/IEC 27001.

\* Please contact our technical support for details that are not provided above, since this technical sheet is based on general conditions. Otherwise, the manufacturer may not be held responsible for any missing information. Our company reserves the right to change the information provided. Where necessary, please refer to the Material Safety Data Sheets for more information on health, safety and handling risks, and precautions associated with the products.